

PRIMAIRE B

Sealing compound

USES

PRIMAIRE B is used as a primer on concrete, asphalt and steel for hot polymer based bituminen products such as ACCOPLAST BSP, ACCOPLAST E or ACCOPLAST N2.

DESCRIPTION

- Ready to use.
- It is applied cold.
- Short drying time.

PROPERTIES

- | | |
|--|-------------------------------------|
| ➤ Density at 23°C (EN ISO 2811) | 0.9 approximately |
| ➤ Viscosity at 25°C (EN ISO 2431) | 45 s approximately (AFNOR cup 3 mm) |
| ➤ Flash point | 23°C |
| ➤ 7 days Persoz hardness (EN ISO 1522) | 55 s approximately |
| ➤ Drying time at 23°C | 1 hour minimum |

DIRECTION FOR USE

Preparation of substrate

- The substrate must be clean, dry and coherent.
- The substrate must be thoroughly prepared.

Application

- Homogenise PRIMAIRE B in cans.
- Apply using a brush or a spray gun.
- It should not be applied too thickly.
- PRIMAIRE B should be totally dry when the compound is applied.
- Consumption: approx. 10 g/ml for a 30 mm deep seal
- Minimum temperature (ambient and substrate) : 5°C and 3°C above the dew point.

Cleaning of equipment

- Before hardening with DILUANT D 752.

PACKAGING

- 4,5 kg
- 25 kg

PRECAUTIONS FOR USE

- The relevant work place hygiene regulations must be strictly adhered to when handling the product: gloves and goggles to be worn.
- Refer to Material Safety Data Sheets for further information.

STORAGE

- At a temperature between 5°C and 35°C, protected from all weather.
- For one year from the date of shipment of the product if stored in its original, unopened packaging.

The information contained herein is indicative only and is based on our knowledge and experience. We reserve the right to change the composition of our products at any time, in the light of the findings of the most recent research. The resulting physical and chemical data will then differ. Variations in quality, size and colour will occur under normal conditions and are acceptable. The information given in our data sheets concerning the use and the application of the product are general rules and cannot, by definition, take account of the specific circumstances of each site. Our guarantee being limited to the quality of the product supplied, INTERDESCO cannot under any circumstances be liable for the correct application of the product to the substrate, over which it has no control. Application must be undertaken by a qualified professional, who shall be required to take account of the data provided by the manufacturer, the professional recommendations issued by the Syndicat National des Formulateurs des Résines de Synthèse, any Unified Technical Documents (D.T.U.) as well as accepted good practice.

The coating applier shall perform in situ tests prior to applying the product.

Any claims relating to the manufacturer's obligation to comply with the specifications must be made after performing in situ testing, and no later than one month after delivery.

Certifié ISO 9001